Pectin-honey hydrogel: Characterization, antimicrobial activity and biocompatibility

(Article begins on next page)

19 July 2019

1   **Pectin-honey hydrogel: characterization, antimicrobial activity and biocompatibility**

2

3   Gessica Giusto[a], Giangiacomo Beretta[b], Cristina Vercelli[a], Emanuela Valle[a], Selina Iussich[a],

4   Roberta Borghi[c], Patrizio Odetti[c], Fiammetta Monacelli[c], Clara Tramuta[a], Elena Grego[a], Patrizia

5   Nebbia[a], Patrizia Robino[a], Rosangela Odore[a], Marco Gandini[a]

6

7   [a] Department of Veterinary Sciences, University of Turin, Largo Paolo Braccini 2-5, 10095

8   Grugliasco (TO), Italy

9   [b] Department of Pharmaceutical Sciences DISFARM, University of Milan, Via Mangiagalli 25,

10   20133 Milano (MI), Italy

11   [c] Department of Internal Medicine and Medical Specialties, University of Genoa, Viale Benedetto

12   XV 6, 16132 Genova (GE), Italy

13

14

15   Address correspondence to Dr. Gandini at marco.gandini@unito.it from the Department of

16   Veterinary Sciences, University of Turin, Largo Paolo Braccini 2-5, 10095 Grugliasco (TO),

17   Italy, phone +390116708861

18

19

20

21

22

23

24

Abstract

Background: Novel pectin-honey hydrogels have been developed and characterized as medical device. Ideally, a wound dressing should maintain optimal fluid affinity, permit moisture evaporation, protect the wound from microbes, and have shape-conformability, biocompatibility, and antibacterial activity. **Objective:** A novel, simple and fast method to produce pectin-honey wound dressings is described. **Methods:** The properties of these pectin-honey hydrogels were investigated, including swelling ability, water vapour transmission rate, hydrogen peroxide production, methylglyoxal content and antibacterial activity. Biocompatibility was assessed by proliferation assays using cultured fibroblast cells and by *in vivo* study with subcutaneous and intraperitoneal implantation in rats. **Results:** Hydrogel showed a good water vapour transmission rate, fluid uptake and were not cytotoxic for fibroblasts. The hydrogel demonstrated good antibacterial activity toward clinically relevant pathogens, including *S. aureus* and *E. coli*. Biocompatibility was confirmed by the measurement of plasma levels of interleukin (IL)1 beta, IL-6, tumour necrosis factor (TNF) alpha, and prostaglandin (PG)E2. No histological changes were observed. **Conclusions:** The presence of a natural active component, conformability, and complete resorbability are the main characteristics of this new biocompatible biomaterial that is well tolerated by the body, possibly improves healing, may be used for surgical complications prevention, with a simple and inexpensive production process.

Introduction

Healing wounds are sites that are easily attacked by bacteria, which leads to the formation of a biofilm that devitalises tissues [1]. The development of a new wound dressing is a focus area for many researchers since the dressing can create a barrier against infection while maintaining a physiological environment in contact with the wound [2-3]. These dressings help to maintain a moist environment at the wound site, promote tissue healing, and reduce infection, pain, and costs [1, 4-5]. Antimicrobial agents play an important role in reducing bacterial contamination, but the resistance of pathogens to these substances has led to a decrease in the efficacy of antibiotics. Researchers have therefore advised against the use of systemic antimicrobial agents for the treatment of wounds [1, 6].

Various wound dressings consisting of vegetable fibres, protective films, hydrogels, and hydrogel enriched with nitrogen oxides are available commercially [1-2, 5, 7]. Hydrogels are reported to be suitable for use in healing wounds but they have limitations in current use, which include a requirement for high frequency of application, inactivation by wound fluids, and formation of eschars [5]. The requirement for a new antimicrobial substance led to revaluation of ancient remedies, including the use of honey [8-9].

Honey has been used alone or in combination with other compounds for medical use since ancient times. Honey is a heterogeneous substance, has antimicrobial activity, anti-inflammatory effects and increase the healing process following skin or peritoneal damage [8, 10]. It contains high levels of glycine, methionine and proline which are all fundamental for collagen formation and fibroblast deposition, which are the main factors for wound healing [11].

Manuka honey, produced in New Zealand, is the most studied honey having antibacterial properties against major aerobic and anaerobic bacteria species [12-13].

72 Several components are known to contribute antibacterial activity of honey. The osmotic effect of

73 the sugars in honey and its characteristically acidic pH are known factors hindering bacterial

74 multiplication. Recently, two components of honey, hydrogen peroxide (H2O2) and

75 methylglyoxal (MGO), have been identified as effective antibacterials [14-16].

76 An ideal wound dressing is yet to be developed. Ideally, a wound dressing should maintain

77 optimal fluid affinity, permit moisture evaporation, protect the wound from foreign microbes, and

78 have shape-conformability, biocompatibility, and antibacterial activity [2,4-5,17].

79 Based on these premises, the aim of the present study was to describe and characterize the

80 properties of pectin-honey hydrogels (PHHs) for wound healing and to assess their

81 biocompatibility through an in vitro and in vivo assay.

82 **Material and methods**

83 *Materials*

84 Honey was purchased from Manuka Health (66 Weona Court,Te Awamutu 3800, New Zealand)

85 and pectin from Ardet s.r.l. (Torino, Italy). Culture media, that is, tryptone soy agar (TSA),

86 tryptone soy broth (TSB), peptone water, and 5% sheep blood agar, were purchased from Oxoid

87 (Milan, Italy). Escherichia coli (Turin strain) and Staphylococcus aureus (Turin strain) isolated

88 from canine wounds were used for this work.

89 *Preparation of PHHs*

90 The preparation method was modified after the procedure described by Walker. (Walker, 1942)

91 [18] Briefly, the pectin-honey hydrogels were prepared starting from a solution (1:1 v/v) of liquid

92 honey (Manuka Health, New Zealand) and sterile deionized water. The same volume of pectin

93 powder (ARDET s.r.l., Italy) was then added and with continuous stirring until the mixture was

94 homogeneous. The resulting gel was spread into 2 mm thick films and hot air dried at 40+/- 0.5

95 °C for 6 h. Then it was cut into squares of 5 x 5 cm and further conditioned in an air drier at 25+/-

96   1 °C for 5 days. The films were then collected and packed in polyethylene under vacuum

97   conditions. All membranes were sterilized by gamma-irradiation at 25 KGray at the Sterigenics

98   Italy (Sterigenics Italy, Minerbio (BO), Italy) [19].

99   *Fluid uptake test (Swelling test)*

100   To investigate the fluid swelling ratio of PHHs, samples were cut into disks with a diameter of

101   approximately 25 mm. The dry weights (Wdry) of the membranes were measured and recorded.

102   Afterwards, pre-weighed dry samples were immersed in PBS solution, pH 7.4, at 37°C. The

103   weights of the swollen PHHs were determined every 5 min subsequently by sandwiching the

104   membranes between two paper towels to remove excess water on the surface, and then wet

105   weights (Wwet) were measured. All experiments were performed in triplicate. The swelling

106   ratios were calculated as the average value according to the following formula:

107   DS = [(Ww – Wd)/Wd] × 100

108   Where Ww and Wd represent the weights of wet and dry samples, respectively.

109   *Water vapour transmission rate (WVTR)*

110   The moisture permeability of the PHH was determined by measuring the WVTR. A piece of the

111   specimen was fixed over the top of a tube (diameter, 34 mm) containing 10 mL PBS. The tube

112   was then placed in an incubator at 37°C and 35% relative humidity. The membranes were

113   weighed at regular intervals of time and the weight loss was recorded and plotted on a graph

114   versus time. The WVTR was calculated from the slope of the graph by the following formula:

115   WVTR g (m2/day) = (slope × 24)/A

116   Where A is area of the sample (m2). Experiments were performed in triplicate.

117   *H2O2 analysis*

118   The analysis of H_2O_2 from honey and PHHs was carried out according to the method reported by

119   Long (1999) [20] (ferrous ion oxidation-xylenol orange [FOX] assay), with minor modifications.

120   The stock reagents were as follows: reagent 1, 4.4 mM butylated hydroxy toluene (BHT) in

121   HPLC-grade methanol; reagent 2, 1 mM xylenol orange and 2.56 mM ammonium ferrous

122   sulphate in 250 mM H_2SO_4; working reagent: one volume of reagent 2 added to nine volumes of

123   reagent 1. Approximately 200 mg of honey were diluted with deionized water to the ratio 20%

124   w/w and immediately kept in a thermostat at T = 37 °C, and 100-µL aliquots were added to 900

125   µl of FOX working reagent. After 20 min of incubation at room temperature, absorbance was

126   measured at λ= 560 nm against a blank comprising 900 µL of working reagent and 100- µL

127   aliquots of distilled water (absorbance of diluted honey was negligible at the operative

128   wavelength). H_2O_2 was monitored at 5, 10, 15, 20, 30, 60, and 120 min and up to 24 and 48 h of

129   incubation.

130   To reduce the processing time required to extract the water-soluble components from PHHs, their

131   size was reduced prior to incubation by cutting the specimens into small pieces with the aid of a

132   small and clean knife. Aliquots of 100 µL of the aqueous layer of the final mixture (40% w/w)

133   were subjected to FOX analysis as described above for honey. Monitoring of $H2O2$ was carried

134   out at 60 min, 90 min, 24 h, and 48 h. The FOX assay was calibrated using standard H2O2

135   (molar extinction coefficient, 43 M-1 cm-1; absorbance wave length of H2O2 λ = 240 nm; linear

136   range, 0–50 µM). Ten units of catalase were sufficient to destroy all the H_2O_2 immediately.

137   Controls with catalase were used to exclude interference due to honey constituents.

138   ***Methylglyoxal (MGO) analysis***

139   MGO was evaluated by the method proposed by Wild (2012) [21] with slight modifications. The

140   method is based on the reaction between N-acetyl-L-cysteine (Sigma Aldrich) and MGO at room

141   temperature. Samples were diluted in water (340 mg/ml) and the reaction was performed in 100

142   mM sodium dihydrogen phosphate buffer (adjusted to pH 7.0 with 10 M NaOH) at 22 °C. For the

143   standard curve of the reaction, different concentrations of MGO (0.5, 1, 2, and 5 mM) were used.

144 MGO solutions (Sigma Aldrich) equivalent to 0.5, 2, and 5 mM and 10 μl of each honey solution

145 (170 mg HBM/ml water) were added up to a volume of 980 μL with sodium dihydrogen

146 phosphate. The reaction was started by adding 20 μL 500 mM N-acetyl-L-cysteine, and the

147 absorption was recorded after 7 min. The condensation product, N-α-acetyl-S-(1-hydroxy-2-oxo-

148 prop-1-yl) cysteine, was determined by recording the absorption at 288 nm (UVIKON 923, Bio-

149 Tek Instrument). Results are given in μmol/mg of honey.

150 ***Protein content analysis of honeys***

151 Honey samples were diluted in water and the protein content was determined using the BCA

152 protein assay kit according to the manufacturer's instructions (Pierce, BCA Protein Assay).

153 ***Microbiological analysis***

154 The success of sterilization was verified by the absence of bacterial growth on solid medium (5%

155 sheep blood agar) at 37 °C for 24 h, both in aerobiosis and anaerobiosis. Subsequently, the

156 antibacterial activity of PHHs was determined against S. aureus and E. coli, which had been

157 previously isolated from canine wound infections. The agar good diffusion method was used to

158 screen the antimicrobial activity of the Manuka PHHs [22]. Clinical strains were grown overnight

159 in TSB at 37°C and adjusted to 0.5 McFarland standard. Each culture was inoculated on the

160 surface of Petri plates. Subsequently, wells with 6-mm diameter were bored into the surface of

161 the agar. The wells were filled with 6 mm of a Manuka honey-based patch, 80 μl of a Manuka

162 honey sample 100% v/v (as positive control), 80 μl of a Manuka honey sample 50% v/v (as a

163 positive control that resembles the concentration of honey present in PHHs), and 6 mm of pectin

164 (as negative control). Plates were incubated at 37°C, and after 24 h, the diameters of the

165 inhibition zones were measured. Each assay was carried out in triplicate.

166 ***In vitro cytotoxicity assay***

167 The cytocompatibility of PHHs was evaluated using L929 cells (mice fibroblasts) (ECACC Cell

168 Lines-Sigma Aldrich, Milan, Italy) that were cultured in 75 mL flasks containing Modified

169 Eagles Medium (MEM; Sigma Aldrich, Milan, Italy), 10% fetal bovine serum (FBS; Sigma

170 Aldrich, Milan, Italy), 2% L-glutamine (Sigma Aldrich, Milan, Italy), and 2% penicillin-

171 streptomicin-amphotericin B solution (Sigma Aldrich) at 37°C with 5% CO_2, 95% air, and

172 complete humidity. When a confluence of 80% was reached, cells were detached using 0.1%

173 trypsin/EDTA solution (Sigma Aldrich, Milan, Italy), centrifuged, and counted using Trypan

174 Blue solution (Sigma Aldrich) with a Burker chamber. Cells were either resuspended at a

175 concentration of 5×105 cells/mL or stored at -80°C for further analysis. The 3-(4,5-

176 dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide (MTT) reduction assay, a routine method

177 for quantifying cell viability, was used [23].

178 Cells (5×10^5 cells/100 µL) were transferred into 96-well plates in order to perform the MTT

179 assay at 24, 48, and 72 hours after seeding. After an overnight incubation at 37°C and 5% CO_2,

180 the medium was changed (MEM, FBS 10%, antibiotic and antimycotic solution 2%, L-glutamine

181 2%), and serial decreasing concentrations of honey membranes dissolved in phosphate buffered

182 saline (PBS) solution, starting from 0.1 g/ml, were added. After adding MTT (Sigma Aldrich,

183 Milan, Italy) solution (4 mg/ml in PBS), the plates were incubated at 37 °C and 5% CO_2 for 4

184 hours. At the end of incubation, the medium was removed, and 100 µL of dimethyl sulfoxide

185 (DMSO; Sigma Aldrich, Milan, Italy) was added in order to lysate the formazan crystals. The

186 plates were further incubated for 10 minutes on a continuous shaker at room temperature, and the

187 optical density of the wells was determined using a plate reader (Poverwave x; Bio-Tek

188 Instruments Inc., Winooski, USA) at a wavelength of 570 nm.

189 ***In vivo biocompatibility study***

190 All procedures were approved by the Bioethical Committee of the University of Turin and by the

191 Italian Ministry of Health (protocol number 304/2015-PR, 20/04/2015).

192 A total of 39 adult male Sprague-Dawley rats, weighing 225-250 grams, were purchased by

193 Harlan Laboratories (Italy). All rats were housed in single cages for 7 days prior to the beginning

194 of the experiment. The room temperature was set at 23°C throughout the duration of the

195 experiment and cages were cleaned daily. Animals were fed with a commercial diet and water

196 was given ad libitum. Anaesthesia was induced by administering 5 mg/kg of xylazine

197 (Rompum®, Bayer Animal Health, Italy) and 50 mg/kg of tiletamine and zolazepam (Zoletil 50,

198 Virbac, Italy) intramuscularly. Anaesthesia lasted for approximately 1 hour. Under anaesthesia,

199 blood samples were collected from the caudal vein to perform biochemical analysis. Soon after,

200 the ventral hair was shaved and the skin was prepared using a 3-step iodopovidone –

201 chlorhexidine scrub. The animals were randomly assigned to the treatment or control groups. A

202 4-cm midline incision was made in the abdominal wall. In the treatment group, subcutaneous and

203 intraperitoneal implantation of PHH was performed as previously described [24]. Briefly, one

204 square each of PHH measuring 1×1 cm was implanted intraperitoneally under the left

205 abdominal wall and subcutaneously at ~1 cm left to the midline between the muscle and skin. In

206 the control group, only the surgical procedure was performed without PHH implantation. In both

207 groups, the midline incision was closed in two layers, with 3-0 USP glycomer 631 for the fascia,

208 and with 3-0 USP nylon for the skin. Each surgical procedure lasted about ~20 minutes.

209 Blood samples for the biochemical analysis were collected from the caudal vein. The blood was

210 collected into tubes before surgery and at 6 h (T6), 24 h (T24), and 72 h (T72) post-surgery and at

211 the time of euthanasia. Plasma levels of IL-1β, IL-6, TNF-α and PG(E2) were measured by using

212 a commercial ELISA kit (Rat IL1 beta ELISA kit, Booster Biological Technology; Rat Il-6

213   ELISA, AB Frontier; Rat TNF alpha ELISA, AB Frontier; Prostaglandin E2 Express EIA kit,

214   Cayman Chemical).

215   At 0, 6, 24, 72 hour's post-surgery, three rats from each group were euthanized and target organs

216   (liver, kidney, left abdominal wall) were collected and fixed in 4% formaldehyde. These tissues

217   were sectioned, stained in H&E, and observed by two pathologists in a blinded manner [24].

218   *Statistical analysis*

219   Normality of the data was evaluated using the Shapiro–Wilk normality test. For the in vitro

220   cytotoxicity assay, all experiments were performed in triplicate, and the data are representative of

221   at least three independent experiments. The results, expressed as mean ± SEM values, were

222   analysed using the Kruskal-Wallis test and a Dunn's post-test.

223   For plasma cytokine levels, all experiments were performed in duplicate. For IL-1β, IL-6, and

224   TNF-α, the results have been expressed as median (95% IC) values and were analysed using the

225   one-way ANOVA test. For PG(E2), the results are expressed as median (95% IC) and were

226   analysed using the Friedman test. Statistical analysis was performed with the GraphPad Prism

227   6.01 software. Values with $p < 0.05$ were considered significant.

228   **Results**

229   *Fluid uptake test (swelling test)*

230   The weight of PHHs immersed in PBS solution under physiological mimicking conditions (pH

231   7.4, 37°C). The fluid content increased to about 150% after 180 minutes. The results from the

232   fluid uptake experiment revealed that the dressing has wide capacity to prevent fluid

233   accumulation if used on wound.

234   *WVTR*

235   The transmission of water vapour through the membranes is an important parameter for the

236   evaluation of their effectiveness as a hydration factor when placed on a wound. The WVTR

237 recommended for wound dressing is 2000–2500 g/m2/day in order to ensure proper wound

238 moisture without risk of dehydration or excessive production of exudates [1,4]. A good WVTR

239 facilitates the healing process because it improves cell migration and promotes re-

240 epithelialization.

241 The water loss from a fully hydrated dressing on exposure to air was evaluated. The mean

242 evaporative water loss from PHHs was 2689.8 ± 158.5 g/m2/day.

243 *H_2O_2-producing activity*

244 All the honey samples, before inclusion in the membranes, were able to produce significant

245 amounts of H_2O_2 while no H_2O_2 development was observed in the case of corresponding PHHs

246 (data not shown). In Manuka honey, at shorter incubation times up to 90 min of incubation, the

247 concentration of H_2O_2 generated by honey glucose oxidase was in the range reported in the

248 literature for other types of honey with different methods of analyses (1–2 mM at 30 min of

249 incubation) [16, 25-27]. By contrast, Manuka honey showed the lowest H_2O_2production at all

250 incubation times, probably because of its high content of MGO, which has previously been

251 suggested to be a glucose oxidase-inhibitory agent [16, 25]. At longer incubation times (24 and

252 48 h), the tested honey samples displayed a significantly different behaviour: The dramatic loss

253 of H_2O_2producing activity found for PHHs indicated that their production procedure, which

254 included a heating step at 80 °C and exposure to γ-rays for final sterilization, induced complete

255 loss of glucose oxidase activity. This demonstrated that the preserved antibacterial activity in the

256 microbiological testing was generated solely by the action of nonperoxide agents.

257 *MGO analysis*

258 Dihydroxyacetone (DHA) is a direct precursor of MG in Manuka honey [15]. The MGO

259 concentration in PHHs, determined by the N-acetyl-L-cysteine assay, was 0.26 ± 0.07 μmol/mg

260 of proteins. The PHHs had higher MG concentration than bulk honey. MGO content is important

261 because it can serve as a suitable quality and cost parameter for Manuka honey. The H_2O_2 and

262 MG content is responsible for the antibacterial activity of honey [28] and PHHs maintain

263 antibacterial activity similar to that of bulk honey.

264 ***Microbiological analysis***

265 Manuka membranes did not show bacterial contamination after sterilization by gamma-

266 irradiation. Table 1 outlines the antibacterial activity based on the clear zone that was produced.

267 ***In vitro cytotoxicity assay***

268 Results concerning the effects induced by different concentrations of dissolved honey membrane

269 on viability of L929 cells are represented in Figure 1.

270 ***In vivo biocompatibility study***

271 Three rats from the treated group died of ascites in the first 24 hours. The gross evaluation in 36

272 rats showed no wound site infection or presence of adhesions. On performing histological

273 analysis 24 and 72 hours' post-surgery, the tissue near the implant was found to be characterized

274 by the presence of fibroblasts with some cellular response, including lymphocytes, macrophages,

275 and neovascularisation. No reaction was observed in distant organs. Thus, the PHHs did not

276 induce a foreign body reaction. The differences in the blood levels of the IL-1β, IL-6, TNF-α and

277 PG(E2) at the 0, 6, 24, and 72 hours' time points were not statistically significant. The results are

278 summarized in Table 2.

279 **Discussion**

280 The new membranes may be used as wound dressings as they have a good WVTR and fluid

281 uptake and show no cytotoxicity to fibroblasts; they also have good swelling capability, which is

282 an important factor for reducing the risk of wound dehydration.

283

284

285 The results obtained by the citoxicity assay after 24 hours from the seeding, in presence of

286 decreasing concentrations of dissolved honey membranes, have shown a statistically significant

287 decrease ($p<0.05$) of the cells treated with the highest concentration (0.1 g/ml) compared to the

288 control ones was observed. At 48 hours a trend in cell proliferation was found: highest

289 concentrations seemed to induce a inhibition in cell growth while decreasing the concentration,

290 the cell proliferation seemed to increase, even if it was not possible to highlight significant

291 differences. Also at this time point it was possible to appreciate a statistically significant

292 decreasing ($p<0.05$) of the cells treated with the highest concentration (0.1 g/ml) compared to the

293 control.

294 After 72 hours of incubation, the highest concentrations (from 1:2 to 1:64) caused an inhibition in

295 cell growth while the lowest (1:256 and 1:512) induces a statistically significant increase in cell

296 growth compared to the control. During the *in vivo* experiments, tree rats died: in authors'

297 opinion, this was because of the excessively large sheet of membrane implanted intraperitoneally

298 because, initially, a dimension of 2×2 cm was chosen. Reducing the dimension of the implanted

299 PHHs to 1×1 cm did not cause any intraperitoneal accumulation of fluid, as determined from

300 macroscopic examination after euthanasia of the remaining rats. The tissue response to

301 intraperitoneal and subcutaneous implants showed a similar macroscopic and histological pattern.

302 In the light of PHHs antibacterial activity [12] and since administration of systemic antibiotics

303 does not always lead to good outcomes in terms of: wound healing, matrix penetration of the EPS

304 biofilm and antibiotic resistance, in this study we propose the use of Manuka honey to prepare

305 PHH for wound dressings. Interestingly, our membranes demonstrate a good antibacterial activity

306 toward clinically relevant pathogenic microorganisms such as S. aureus and E. coli.

307 Honey membranes possess a wide variety of properties that can make them suitable (as for other

308 natural materials such as chitosan hydrogels) [2, 24, 29], for very different uses that we can

hypothesise ranging from wound healing to adhesion prevention to drug delivery. The presence of natural active components, conformability, and complete resorbability are the main characteristics of this new biocompatible biomaterial that respects the pathophysiology of tissue, is well tolerated by the body, possibly improves healing, and may be used for the prevention of surgical complications. Furthermore, the production of these devices is extremely simple and inexpensive.

Acknowledgments

References

1. Dave RN, Joshi HM, Venugopalan VP. Biomedical evaluation of a novel nitrogen oxides releasing wound dressing. J Mat Sci: Mat Med 2012; 23: 3097–3106.

2. Shahzad S, Yar M, Siddiqi SA, Mahmood N, Rauf A, Qureshi ZA, et al. Chitosan-based electrospun nanofobrous mats, hydrogels and cast films: novel anti-bacterial wound dressing matrices. J Mater Sci Mater Med 2015; 26: 136-148.

3. Zhou G, Ruhan A, Ge H, Wang L, Liu M, Wang B, et al. Research on a novel poly (vinyl alcohol)/lysine/vanillin wound dressing: Biocompatibility, bioactivity and antimicrobial activity. Burns 2014; 40: 1668-1678.

4. Archana D, Singh BK, Dutta J, Dutta PK. Chitosan-PVP-nano silver oxide wound dressing: In vitro and in vivo evaluation. Int J Biol Macromol 2015; 73, 49–57.

5. Das A, Kumar A, Patil NB, Viswanathan C, Ghosh D. Preparation and characterization of silver nanoparticle loaded amorphous hydrogel of carboxymethylcellulose for infected wounds. Carbohydr Polym 2015; 130: 254-261.

6. Godlee F. Antimicrobial resistance – an unfolding catastrophe. Br Med J 2013; *346*: f1663.

333   7. Harkins A, Duri S, Kloth LC, Tran CD. Chitosan-cellulose composite for wound dressing

334   material. Part 2. Antimicrobial activity, blood absorption ability, and biocompatibility. J

335   Biomed Mat Res Part B: Appl Biomat 2014; 102: 1199-1206.

336   8. Cooke J, Dryden M, Patton T, Brennan J, Barrett J. The antimicrobial activity of

337   prototype modified honeys that generate reactive oxygen species (ROS) hydrogen

338   peroxide. BMC Res Not 2015; 8: 1-5.

339   9. Sarhan WA, Azzary ME (2015) High concentration honey chitosan electrospun

340   nanofibers: Biocompatibility and antibacterial effects. Carbohydr Polym 2015; 122: 135-

341   143.

342   10. Emre A, Akin M, Isikgonul I, Yuksel O, Anadol AZ, Cifter C. Comparison of

343   intraperitoneal honey and sodium hyaluronate-carboxymethylcellulose (Seprafilm™) for

344   the prevention of postoperative intra-abdominal adhesions. Clin 2009*; 64:* 363-368.

345   11. Tan MK, Adli DSH, Tumiran MA, Abdulla MA, Yusoff KM. (2012) The efficacy of

346   gelam honey dressing towards excisional wound healing. Evid Based Complement

347   Alternat Med 2012; 2012: 805932.

348   12. Arne S, Kai S, Gertrud W, Gisela B, Udo B, Gudrun F. Wound care with antibacterial

349   honey (Medihoney) in pediatric hematology-oncology. J Supp Care Cancer 2006; 14: 91-

350   97.

351   13. Snow MJ, Manley-Harris M. On the nature of non-peroxide antibacterial activity in New

352   Zealand manuka honey. Food Chem 2004; 84: 145-147.

353   14. Çalamak S, Erdogdu C, Ozalp M, Ulubayram K. Silk fibroin based antibacterial

354   bionanotextiles as wound dressing materials. Mat Sci Eng C 2014; 43: 11–20.

355   15. Atrott J, Harberlau S, Henle T. Studies on the formation of methylglyoxal from

356   dihydroxyacetone in Manuka (Leptospermum scoparium) honey. Carbohydrate Research

357   2012;361:7–11.

358   16. Kwakman PHS, teVelde AA, de Boer L, Vandenbroucke-Grauls CM, Zaat SAJ. Two

359   major medicinal honeys have different mechanisms of bactericidal activity. PLoS ONE

360   2012; 6: e17709.

361   17. Shi L, Yang N, Zhang H, Chen L, Tao L, Wei Y, et al. A novel poly(γ-glutamic

362   acid)/silk-sericin hydrogel for wound dressing: Synthesis, characterization and biological

363   evaluation. Mat Sci and Eng: C 2015; 48: 533-540.

364   18. Walker JE. Method of preparing homogeneous honey pectin composition. Patented 1942;

365   September 8.

366   19. Carnwath R, Graham EM, Reynolds K, Pollock PJ. The antimicrobial activity of honey

367   against common equine wound bacterial isolates. Vet J 2014; 199: 110-114.

368   20. Long LH, Lan ANB, Hsuan FTY, Halliwell, B. Generation of hydrogen peroxide by

369   "antioxidant" beverages and the effect of milk addition. Is cocoa the best beverage? Free

370   Radic Res 1999; 31: 67–71.

371   21. Wild R, Ooi L, Srikanth V, Münch G. A quick, convenient and economical method for

372   the reliable determination of methylglyoxal in millimolar concentrations: the N-acetyl-L-

373   cysteine assay. Anal Bioanal Chem 2012; 403: 2577–2581.

374   22. Sherlock O, Dolan A, Athman R, Power A, Gethin G, Cowman S, et al. Comparison of

375   the antimicrobial activity of Ulmo honey from Chile and manuka honey against

376   methicillin-resistant Staphylococcus aureus, Escherichia coli and Pseudomonas

377   aeruginosa. BMC Complement Altern Med 2010; 47: 354–361.

378   23. Vercelli C, Barbero R, Re G. Transient receptor potential Vanilloid 1 in animal tissue: an

379   overview to highlight similarities and differences with human species. Recept Clin Invest

380   2015; 2: 1-9.

381   24. Azab AK, Doviner V, Orkin B, Kleinstern J, Srebnik M, Nissan A, et al.

382   Biocompatibility evaluation of crosslinked chitosan hydrogels after subcutaneous and

383   intraperitoneal implantation in the rat. J Biomed Mat Res 2007; 83: 414-422.

384   25. Majtan J, Bohova J, Prochazka E, Klaudiny J. Methylglyoxal may affect hydrogen

385   peroxide accumulation in manuka honey through the inhibition of glucose oxidase. J

386   Med Food 2014; 17: 290–293.

387   26. Brudzynski K, Abubaker K, St-Martin L, Castle A. Re-examining the role of hydrogen

388   peroxide in bacteriostatic and bactericidal activities of honey. Front Microbiol 2011; 2: 1-

389   9.

390   27. Bang LM, Buntting C, Molan P. The effect of dilution on the rate of hydrogen peroxide

391   production in honey and its implications for wound healing. J Alter Compl Med 2003; 9:

392   267–273.

393   28. Yusof N, Hazifa A, Zohdi RM, Bakar ZA. Development of honey hydrogel dressing for

394   enhanced wound healing. Rad Physic Chem 2007; 76: 1767–1770.

395   29. Zhang ZL, Xu SW, Zhou XL. Preventive effects of chitosan on peritoneal adhesion in

396   rats. World J Gastroenterol 2006; 12: 4572-4577.

397   **Table legend**

398   Table 1: Mean zones of inhibition (diameter [including that of the well], 6 mm)

399   Table 2: Results for blood levels of the IL-1β, IL-6, TNF alpha and PG(E2)

400   **Figure legend**

401 Figure 1: MTT assay (N=8) to evaluate the modulation of L292 cells growth after the treatment

402 with decreasing concentrations of dissolved honey membrane in PBS at different experimental

403 time points (24, 48, and 72 hours).